



Biobacta



Journal of Bioscience and Applied Research

WWW.JBAAR.ORG



green synthesis and characterization of iron-oxide nanoparticles by guava aqueous leaves extract for doxorubicin drug loading

Moustafa Hussein Moustafa^{1*}, Rasha shams Al Din²

Biophysics Department, Medical research institute^{1,2}

(*Email: Moustafa-hm@alexu.edu.eg)

DOI: 10.21608/jbaar.2017.126138

Abstract

Green biosynthesis of iron oxide nanoparticles (Fe_3O_4 Nps) was carried out in one step. An aqueous extract of orange peels, green tea, and guava leaves was utilized as a precipitating agent for metal precursors. The guava leaves extract was the most powerful one. The shape and size of (Fe_2O_3 Nps) were monitored by transmission electron microscopy. The existence of iron in the yield was studied by UV-visible spectroscopy. The stability of the particles was estimated by hydrogen peroxide reaction. The (Fe_3O_4 Nps) were incubated with human red blood cells (RBCs). the osmotic fragility test for (RBCs) showed no significant shifting from the control. The loading of doxorubicin cytotoxic drug was primitively monitored by scanning electron microscopy for the further study plan.

Keywords: iron-oxide nanoparticles, green biosynthesis, doxorubicin

1 Introduction

Iron-oxide nanoparticles (Fe_3O_4 NPs) have become strong candidates for much biomedical application due to, their small sizes besides the magnetic properties (Monalisa P et al., 2013)^{1,2}. It is important to choose the raw material for (Fe NPs) preparation otherwise the methods for the adjustable physical and chemical properties of interest. Among the methods of preparation for these (Fe NPs) co-precipitation, thermal decomposition sonochemical methods are the most. Besides electrochemical and green syntheses are introduced by many researchers (Akl M et al., 2012)³.

The chemical synthetic procedures generate hazardous by-products that could affect the environment directly. Thus there is a great requirement for green chemistry that includes methods that are environment friendly¹. Hence nowadays many researchers are diverting themselves towards biological systems mostly plants for nanoparticle synthesis as it is cost-effective and can be easily scaled up to be used for large-scale production (Iyer A et al., 2009)^{1,4}.

The cellular extracts from these biological organisms (such as plants and micro-organisms) can be used to synthesize nanoparticles of different sizes and chemical compositions as they contain certain oxidizing compounds like polyphenol which can reduce metal ion precursors whereas water-soluble heterocyclic components stabilize the metal nanoparticles formed. This Biosynthesis of metal nanoparticles extracted from different parts (mostly leaf) of the plant is the most effective process of synthesis at a very affordable cost¹⁻⁵

Entrapping nanoparticles with drugs is a great challenge nowadays. FDA approved doxorubicin hydrochloride drug as liposome-based has been used for the treatment of cancer (Xu et al., 2013)⁶. In the current work, we utilize the aqueous Guava leaves extract to produce iron-oxide nanoparticles. The shape and size of these Fe NPs are observed by Transmission electron microscopy. The Doxorubicin drug was loaded on the prepared MNPs and the rate of drug loading efficiency was evaluated.

2 Materials and Methods

Preparation of plant extract

Fresh Leaves of guava, green tea, and orange plants were collected from the local markets in Alexandria city, Egypt. the leaves were washed twice with distilled water after that they were left to dry. 200 mg

Osmotic fragility test

The fragility of red blood cells (RBCs) was estimated after incubation of the cells with iron-oxide nanoparticles. The osmotic fragility was adopted from H. A. Massaldi, et al incubated with BSR20 ul of .¹²⁾ different concentration of Fe₃O₄ nanoparticles for about 6 hours at 37 °C was added to a serial dilution of normal physiological saline solution with different osmolality % from the following Equation 2:

Hemolysis% = $\frac{\text{absorbance of the test}}{\text{absorbance of complete hemolysis}} \times 100$ The fragility of red blood cells (RBCs) was estimated after incubation of the cells with iron-oxide nanoparticles. The osmotic fragility was adopted from H. A. Massaldi, et al). 20 ul of RBS incubated with different concentration of Fe₃O₄ nanoparticles for about 6 hours at 37 °C was added to a serial dilution of normal physiological saline solution with different osmolality % from the following Equation 2:

DOXO drug loading to MNPs

Loading procedure was adopted from (Davaran et al., 2012)¹³. 2 ml of DOXO. was added to 1 gm of dried MNPS. The mixture was stirring magnetically for 24 hours at room temperature .the Doxo-loaded MNPs was separated with centrifugation for further analysis.The percent of Doxo.loading were deduced by the relation Equation 3

• Doxo.loading efficiency = $\frac{\text{weight of Doxo. after incubation}}{\text{weight initial Doxo.}}$ The percent of Doxo.loading were deduced by the relation Equation 3




Figure 3: Graphic distribution of absorbance versus the corresponding wavelength showing the maximal absorbance peak.

Fe₃O₄ NPs -H₂O₂ oxidation

Nanoparticle resistance to oxidation was measured by UV-vis before and after the addition of 100 µl of 30% H₂O₂ to 5ml nanoparticle suspension for five minute. as shown in **Figure 3**, there is no shift in absorbance peak neither plain Fenps or Fe-Doxo Nps^{3,14}.




Figure 4:graphical representation of hemolysis percentage of RBCs versus concentration rang of normal saline for control (plain RBCs) and RBCs incubated with Fe₃O₄ of 0.1, 0.2 , and 0.3 % (v/v).the tests were replicated twice represented as mean±SD and pvalue>0.05.

The peaks at 1540 and 1105 cm⁻¹ are attributed to the asymmetric and symmetric stretching vibration of COO⁻¹⁰.The band at 1105.99 cm⁻¹ can be assigned to the symmetric C–O vibration associated with aC–O–SO₃ group . In addition, signals at 3698 cm⁻¹ (OH stretching) and 2358 ad 23269 cm⁻¹ (CH stretching) were also observed^{10,15}.

The presence of magnetite nanoparticles can be seen by two strong absorption bands at around 398 , 380, and 362 cm-1 which **Figure 2**, corresponding to the Fe-O stretching band of bulk magnetite (Fe₃O₄)¹⁶. These results revealed that the C=O groups were bonded on the magnetite particle surface. Overall the observation confirms the presence of organic compounds in guava leaf extract, which acts as a reducing agent and stabilizer for magnetite nanoparticles. These results are in co-ordinance with the results of Mahnaz M et al.^{10,7}

The osmotic fragility results are represented in **Figure 4**. there is no significant skewness of the graph and control graph without Fe₃O₄ NPs .this finding may support that Fe₃O₄ NPs have no osmotic stress on the RBCs integrity under these conditions.

Acknowledgement

From my deep heart I would like to appreciate the valuable advices and scientific guidance of Dr. Mohamed Abdel Aziz AlBelbesy in the experimental design of this work.

5 References

1 Demir, A., Topkaya, R. and Baykal, A. (2013). Green synthesis of superparamagnetic Fe₃O₄ nanoparticles with maltose: Its magnetic investigation. Polyhedron, 65, pp.282-287.

- 2 J.Ngenefeme, F., J. Eko, N., D. Mbom, Y., D. Tantoh, N. and M. Rui, K. (2013). A One Pot Green Synthesis and Characterisation of Iron Oxide-Pectin Hybrid Nanocomposite. *Open Journal of Composite Materials*, 03(02), pp.30-37.
- 3 M. Awwad, A. and M. Salem, N. (2013). A Green and Facile Approach for Synthesis of Magnetite Nanoparticles. *Nanoscience and Nanotechnology*, 2(6), pp.208-213.
- 4 Wang, Z., Zhu, H., Wang, X., Yang, F. and Yang, X. (2009). One-pot green synthesis of biocompatible arginine-stabilized magnetic nanoparticles. *Nanotechnology*, 20(46), p.465606.-
- 5 Mahdavi, M., Namvar, F., Ahmad, M. and Mohamad, R. (2013). Green Biosynthesis and Characterization of Magnetic Iron Oxide (Fe₃O₄) Nanoparticles Using Seaweed (*Sargassum muticum*) Aqueous Extract. *Molecules*, 18(5), pp.5954-5964.
- 6 XU, L., LI, H., WANG, Y., DONG, F., WANG, H. and ZHANG, S. (2013). Enhanced activity of doxorubicin in drug resistant A549 tumor cells by encapsulation of P-glycoprotein inhibitor in PLGA-based nanovectors. *Oncology Letters*, 7(2), pp.387-392.
- 7 Mahdavi, M., Namvar, F., Ahmad, M. and Mohamad, R. (2013). Green Biosynthesis and Characterization of Magnetic Iron Oxide (Fe₃O₄) Nanoparticles Using Seaweed (*Sargassum muticum*) Aqueous Extract. *Molecules*, 18(5), pp.5954-5964
- 8 Von White, G., Kerscher, P., Brown, R., Morella, J., McAllister, W., Dean, D. and Kitchens, C. (2012). Green Synthesis of Robust, Biocompatible Silver Nanoparticles Using Garlic Extract. *Journal of Nanomaterials*, 2012, pp.1-12.
- 9 Kaur, C. and Kapoor, H. (2002). Anti-oxidant activity and total phenolic content of some Asian vegetables. *International Journal of Food Science and Technology*, 37(2), pp.153-161.
- 10 M. Awwad, A. and M. Salem, N. (2013). A Green and Facile Approach for Synthesis of Magnetite Nanoparticles. *Nanoscience and Nanotechnology*, 2(6), pp.208-213.
- 11 Venkatpurwar, V. and Pokharkar, V. (2011). Green synthesis of silver nanoparticles using marine polysaccharide: Study of in-vitro antibacterial activity. *Materials Letters*, 65(6), pp.999-1002.
- 12 H. A. Massaldi, G. V. Richieri, H. C. Mel.(1988) . Osmotic fragility model for red cell Populations. *BIOPHYS. J.*57,pp301-308.
- 13 Davaran, S., Asgari, D., Davaran, S., Akbarzadeh, A., Zarghami, Mikaeili, H. and Mohamad, R. (2012). Preparation and in vitro evaluation of doxorubicin-loaded Fe₃O₄ magnetic nanoparticles modified with biocompatible copolymers. *International Journal of Nanomedicine*, p.511.
- 14 Von White, G., Kerscher, P., Brown, R., Morella, J., McAllister, W., Dean, D. and Kitchens, C. (2012). Green Synthesis of Robust, Biocompatible Silver Nanoparticles Using Garlic Extract. *Journal of Nanomaterials*, 2012, pp.1-12
- 15 Sangeetha, N., Manikandan, S., Singh, M. and K. Kumaraguru, A. (2012). Biosynthesis and Characterization of Silver Nanoparticles Using Freshly Extracted Sodium Alginate from the Seaweed *Padina tetrastratica* of Gulf of Mannar, India. *Current Nanoscience*, 8(5), pp.697-702.
- 16 Qiu, X. (2010). Synthesis and characterization of magnetic nano particles. *Chinese Journal of Chemistry*, 18(6), pp.834-837.